


## FL619ASC

<b>Lucida</b>	Ungalvanized
<b>Anima tessile</b>	Fiber core
<b>Crociata destra</b>	Right Regular Lay
<b>Crociata sinistra</b>	Left Regular Lay
<b>Resistenza 1370/1770 N/mm<sup>2</sup></b>	Tensile rope grade 1370/1770 N/mm <sup>2</sup>
<b>EN 12385-5</b>	EN 12385-5



6(9+9+1)S+FC  
114 fili/wires

Codice Code	Diametro funo Rope diameter	Sezione metallica Metallic cross section	Diametro fili esterni Outer wires diameter	Peso per metro Weight for meter	Carico rottura minimo MBL	
					kN	kg
FL619ASD08	8	25,8	0,65	0,240	31,70	3233
FL619ASD09	9	32,3	0,70	0,298	40,10	4089
FL619ASD10	10	39,5	0,78	0,365	49,50	5048
FL619ASD11	11	48,0	0,87	0,440	59,90	6108
FL619ASD12	12	57,2	0,95	0,530	71,30	7271
FL619ASD13	13	67,2	1,02	0,620	83,70	8535